



E-BX 1200

Fiber Type: E-Glass
 Architecture: +45°/-45° Double Bias
 Dry Thickness: 0.016 in. / 0.40 mm
 Total Weight: 12.54 oz/sq.yd / 425 g/sq.m



Roll Specifications

Roll Width: 50 in / 1270 mm
 Roll Weight: 227 lb / 103 kg
 Roll Length: 196 yd / 179 m

Fiber Architecture Data

0 ° : n/a
 45 ° : 6.27 oz/sq.yd / 213 g/sq.m
 90 ° : n/a
 - 45 ° : 6.27 oz/sq.yd / 213 g/sq.m
 Chopped Mat : n/a

1: Packaging: box or bag.

2: Weights do not include polyester stitching.

Laminated Properties

45 °

45 °

Laminate Weight (lb/sq.ft)		
	E-BX 1200 Resin Infused	E-BX 1200 Open Mold
Fiber	0.09	0.09
Resin	0.04	0.07
Total	0.12	0.16

Physical Properties

	E-BX 1200 Resin Infused	E-BX 1200 Open Mold
Density (g/cc)	1.90	1.69
Fiber Content (% by Wt.)	70%	55%
Thickness (in)	0.013	0.018

Laminate Moduli		
(MSI)	E-BX 1200 Resin Infused	E-BX 1200 Open Mold
Ex	3.90	2.82
Ey	3.90	2.82
Gxy	0.58	0.38
Ex,flex.	3.64	2.63
Ey,flex.	3.64	2.63

Ultimate Stress		
(KSI)	E-BX 1200 Resin Infused	E-BX 1200 Open Mold
Long. Ten.	74	53
Long. Comp.	74	53
Trans. Ten.	74	53
Trans. Comp.	74	53
In-Plane Shear	12	8
Long. Flex.	93	67
Trans. Flex.	93	67

In-Plane Stiffness, "EA"		
10 ³ lb/in	E-BX 1200 Resin Infused	E-BX 1200 Open Mold
(EA)x	49	51
(EA)y	49	51
(GA)xy	7	7

Ultimate In-Plane Load		
lb/in	E-BX 1200 Resin Infused	E-BX 1200 Open Mold
Long. Ten.	931	962
Long. Comp.	931	962
Trans. Ten.	931	962
Trans. Comp.	931	962
In-Plane Shear	146	136

Notes:

- 1: Resin infused laminate made with vinyl ester resin 200 cps viscosity @ 77° F.
- 2: Open mold laminate made with polyester resin.
- 3: All standard reinforcements should be infused with a flow aid or Vectorfusion® reinforcements.



3500 Lakewood Dr. Phenix City, AL 36867 tel. 334 291 7704 fax. 334 291 7743

Disclaimer:

As a service to customers, Vectorply Corporation ("VP") may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by VP in combination with other materials or systems.

VP makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by VP. Specifications of reinforcements may change without notice.