

5700 Skylab Road Huntington Beach CA 92647 USA Phone : +1 714-899-8100 Fax : +1 714-899-8179 E-mail : airtech@airtechintl.com Website : www.airtechonline.com

**Data Sheet** 

# **RELEASE EASE® 234 TFP**

Porous PTFE coated fiberglass fabric

## DESCRIPTION

Release Ease® PTFE coated fiberglass fabrics will provide release from all conventional resin systems. Porous products will allow excess resin, volatiles and trapped air to escape into the breather during cure while non-porous products will retain resin. Release Ease® products have a continuous service temperature to 550°F (288°C).

### BENEFITS

- Porous PTFE coating makes fabric much easier to remove off of cured laminates, resulting in time saved.
- Release Ease strips off cured laminates leaving a textured surface, reducing time spent hand finishing.
- Fiberglass retains its strength through high temperature use for easier removal after cure.

#### **TECHNICAL DATA**

Maximum use temperature Fiber type Thickness Color Coating type Shelf life 550°F (288°C) Fiberglass 0.0024 inch (0.060 mm) Brown PTFE Unlimited when stored in original packaging at 72°F (22°C)

#### SIZES

Width	Length	Packaging
38 inches (97 cm)	100 yards (91 m)	1 roll
50 inches (127 cm)	100 yards (91 m)	1 roll
60 inches (152 cm)	100 yards (91 m)	1 roll

• Other sizes available on special request. Minimum order may apply.

## **NOTES**

- The maximum use temperature is dependent upon the duration at maximum temperature and is process specific, Airtech recommends testing prior to use.
- Color is subject to slight variation and does not affect performance.
- Hot knife (sealed edge) slitting upon request with 1 roll minimum order quantity.

Last updated : 2018-10-09

Catalog position : Release fabrics / Peel plies

As the conditions or methods of use, including storage, are beyond our control, Airtech International, Inc. does not assume any responsibility for the performance of his material for any particular use. The material is sold "as is". Airtech International, Inc. disclaims, and buyer waives, any and all implied warranties, including without limitation the implied warranties of merchantability and of fitness for particular use. The information contained herein represents typical properties and should not be used for specification purposes. Any translation is provided for your convenience only. The official language is English and the official law is California, USA.