

Tenax® - J	HTS40 E13 3K 200tex (G30-500 3K HTA-7C EP03)
	HTS40 E13 6K 400tex (G30-500 6K HTA-7C EP03)
	HTS40 E13 12K 800tex (G30-500 12K HTA-7C EP03)
Tenax® - E	HTS40 F13 12K 800tex (HTS5631 800tex f12000 t0)
	HTS40 F13 24K 1600tex (HTS5631 1600tex f24000 t0)

HTS40 is a family of high strength/standard modulus aerospace grade carbon fibers made in Japan (E13-sized products) and Germany (F13-sized product) for use as reinforcement in high performance composites. These fibers are produced from poly-acrylonitrile (PAN) precursor and are surface treated to promote adhesion to organic matrix polymers. Sizing materials are designed to aid in handling.

Typical Fiber Properties (Lot Average)		Inch-Pound	SI
Tensile strength*	3K E13 (EP03)	620 ksi	4275 MPa
	6K E13	630 ksi	4345 MPa
	12K E13	615 ksi	4240 MPa
	12K/24K F13 (F301)	670 ksi	4620 MPa
Tensile modulus*	3K/6K/12K E13	34.4 Msi	237 GPa
	12K/24K F13	34.7 Msi	239 GPa
Elongation*		1.80%	
Density		0.064 lb/in ³	1.76 g/cc
Yield/Linear density (with sizing)	3K E13 (EP03)	2444 yd/lb	203 tex (g/km)
	6K E13	1219 yd/lb	407 tex
	12K E13	612 yd/lb	810 tex
	12K F13 (F301)	620 yd/lb	800 tex
	24K F13	310 yd/lb	1600 tex
Sizing level w/w	3K/6K/12K E13 (EP03)	1.28%	
	12K/24K F13 (F301)	0.97%	
<u>Yarn / Tow Characteristics</u>			
Filament Diameter		7.0 x 10 ⁻⁶ m	
Twist		Never Twisted	

* Toho Tenax Impregnated Strand Test Method. Based on JIS R7601.

For Technical Assistance Contact
Toho Tenax America, Inc.
18552 MacArthur Boulevard, Suite 325
Irvine, CA 92612-1232, USA
(949) 474-3278 Ext 25

To the best of Toho Tenax's knowledge the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy or completeness of such information. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible long-term adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones which exist. Final determination of the suitability of any information or product for the use contemplated by any user, the matter of that use and whether any infringement of patents is the sole responsibility of the user. We recommend that anyone intending to rely on any recommendation or to use any equipment or processing technique or material mentioned in this publication should satisfy himself as to such suitability and that he can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturers' or suppliers' current instructions for handling each material they use.

RECOMMENDED STORAGE AND SHELF LIFE

A HTS Carbon Fiber Properties

Filament tensile strength, modulus of elasticity, coefficient of expansion, electric and thermal conductivities and yield are inherent properties of the HTA fiber and have indefinite shelf life.

B. HTS Carbon Fiber Processing

Typically, the original processing characteristics of E13 (EP01) and F13 (F301) sized yarn will be essentially constant for at least one year from date of delivery. The product should be stored indoors. The recommended storage conditions are 40°F-77°F (5°C-25°C) and less than 50 percent RH. Direct exposure to sunlight or rain should be avoided. The shrink wrap should not be removed until immediately prior to use.

If the roving is stored at high temperatures and/or high humidity conditions, it may become difficult to process. Roving that stiffens during storage should still be useable. However, a thorough evaluation of the processing characteristics (e.g., resin wet out, spreadability) relative to the customer's operation is strongly recommended.

STANDARD PACKAGING AND SPOOL BUILD

Spool designation	“A”		“B”		“Z”		“H”	
	English	Metric	English	Metric	English	Metric	English	Metric
Net Weight	2.2 lb	(1 kg)	4.41 lb	(2 kg)	< 2.2 lb	(< 1 kg)	8.82 lb	(4 kg)
Tube Length	11.0 in	(27.9 cm)	11.0 in	(27.9 cm)	11.0 in	(27.9 cm)	11.0 in	(27.9 cm)
Tube I.D.	3.0 in	(7.6 cm)	3.0 in	(7.6 cm)	3.0 in	(7.6 cm)	3.0 in	(7.6 cm)
Tube weight	6.0 oz	(170g)	6.0 oz	(170g)	6.0 oz	(170g)	6.0 oz	(170g)
Stroke	10.0 in	(25.4 cm)	10.0 in	(25.4 cm)	10.0 in	(25.4 cm)	10.0 in	(25.4 cm)
Outside dia. (OD)	4.75±0.2 in	(12.1±0.5 cm)	5.0±0.25 in	(12.7±0.6 cm)	Varies		6.4±0.3 in	(16.3±0.8 cm)
Pallet Type	Carton		Carton		Carton		Carton	
Nominal length	5400 yd	(4938 m)	5400 yd	(4938 m)	Non-metered		5400 yd	(4938 m)
No. spools per carton	20		12		Varies		6	
Carton weight	44.1 lb	20 kg	52.9 lb	24 kg	Varies		52.9 lb	24 kg
Carton dimensions (LxWxH)	24.8 x 20.1 x 11.6 in	63 x 51 x 29.5 cm	Same		Same		21.7 x 14.6 x 11.6 in	55 x 37 x 29 cm
Pallet dimensions (LxWxH)	40.6 x 50.8 x 41.5 in	103 x 129 x 105 cm	Same		Same		44.9 x 31.9 x 37.2 in	114 x 81 x 94 cm
Approx. Pallet weight	529 lb	240 kg	635 lb	288 kg	Varies		635 lb	288 kg

Notes:

- “A” spool is standard for 3K, “B” spool for 6K and “H” spool for 12K/24K. “Z” spool is un-metered.
- 12-14 cartons per pallet. Height of pallet not included in dimensions. The pallet size may be changed without notice.

AMERICAS

Toho Tenax America, Inc
121 Cardiff Valley Road
Rockwood
TN 37854-4134
Tel (800) 252-3001 or (865) 354-8408
<http://www.tohotenaxamerica.com>

ASIA

Toho Tenax Co. Ltd.
Kasumigaseki Common Gate West Tower
3-2-1 Kasumigaseki, Chiyoda-ku
Tokyo 100-8585 Japan
Tel +81 (3) 3506-6506
<http://www.tohotenax.com>

EUROPE

Toho Tenax Europe GmbH
Kasinostraße 19-21
Wuppertal 42103
Germany
Tel +49 (202) 322339
<http://www.tohotenax-eu.com>

To the best of Toho Tenax's knowledge the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy or completeness of such information. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible long-term adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones which exist. Final determination of the suitability of any information or product for the use contemplated by any user, the matter of that use and whether any infringement of patents is the sole responsibility of the user. We recommend that anyone intending to rely on any recommendation or to use any equipment or processing technique or material mentioned in this publication should satisfy himself as to such suitability and that he can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturers' or suppliers' current instructions for handling each material they use.