



INNOVATIONS FOR LIVING™

## 158B

### Single End Roving for Filament Winding and Pultrusion

#### PRODUCT DESCRIPTION

Single-End Rovings are produced by pulling individual fibers directly from the bushing and winding them onto a roving package ready for shipment. The uniform distribution of a proprietary sizing system ensures an excellent resin-to-glass binding through uniform distribution of the binding agent. This results in maximum strand integrity.

Single-End Rovings are manufactured using the T30® Roving state-of-the-art technology of Owens Corning, in conjunction with statistical process control in manufacturing facilities certified to ISO 9001.

#### PRODUCT APPLICATION

158B is specifically designed for use in filament winding and pultrusion applications with epoxy resin systems. It is also suitable to reinforce phenolic resins.

158B is the recommended product to be used in applications demanding excellent burst strength. It is approved for use in high pressure vessels.

Advantex® Glass is an Owens Corning patented glass formulation, which meets ASTM D 578 and ISO 2078, as a boron-free corrosion resistant E-CR glass fiber. Advantex® Glass has been providing superior corrosion resistance vs. standard E-glass, since 1996, leading to longer part life and greater service life strength in applications facing corrosion, opening new markets for composites and our customers. Advantex® glass fiber reinforcements combine the electrical and mechanical properties of traditional E-glass with the acid corrosion resistance of E-CR glass. For additional information on Advantex® use the link below.

<http://composites.owenscorning.com/aboutAdvantex.aspx>



© JLSponga

#### FEATURES AND PRODUCT BENEFITS

- |   |   |
|---|---|
| • Excellent Processing  | • Low fuzz properties which equate to smoother parts, less cleanup and improved machine efficiency  |
|   | • Excellent package run out   |
|   | • Virtually 100% transfer efficiency with Tack-Pak® packaging   |
| • Fast Wet Out  | • Fast and Uniform wet-out allow to optimize part fabrication time, increasing productivity.  |
| • Superior burst  | • The 158B provides high burst pressure in pipe or vessels, which allows it to be recommended for use in pressure vessels applications  |
| • Available globally  | • Global manufacturers can use product in all regions resulting in lower design and qualifications costs.   |
| • Superior corrosion resistance with Advantex® Glass compared to standard E-glass | • Advantex® Glass provides superior corrosion resistance vs. standard E-glass, leading to longer part life and greater service life strength in applications facing corrosion |

# 158B

## Single-End Roving for Filament Winding and Pultrusion

### PRODUCT AVAILABILITY

Yield	Tex
225, 250, 450, 675	1100, 2000, 2400

### MECHANICAL PROPERTIES

The following data was generated using Anhydride/Epon 828 Epoxy resin

Strand Tensiles : ASTM D 2343	Strength (MPa)	Strength (Ksi)
158B 450 Yield (1100 tex)	2410	350
158B 250 Yield (2000 tex)	2450	355

Interlaminar Shear Strength NOL ring : ASTM D 2344	Dry shear strength (MPa)	Dry shear strength (psi)	shear strength Retention 72 hr boil (%)
158B 450 Yield (1100 tex)	69.8	10120	95.2
158B 250 Yield (2000 tex)	68.3	9910	93

### PACKAGING

Rovings are available in a single-end internal-pull package. Each pallet weighed about 1 ton. Pallets are stretch wrapped for load stability. All doffs are wrapped with Tack-Pak<sup>®</sup> or shrinkable film for protection during transport. Full doffs are available in weights between 20 kg (44 lb.) and 28 kg (62 lb.) and they can be packaged in bulk or Creel-Pak<sup>®</sup> format. More information is available in the Customer Acceptance Standards.

### STORAGE

It is recommended to store glass fiber products in a cool, dry area. The glass fiber products must remain in their original packaging material until the point of usage; the product should be stored in the workshop, within its original packaging, 48 hours prior to its utilization, to allow it to reach the workshop temperature condition and prevent condensation, especially during cold season. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water.

When stored properly, there is no known shelf life to the product, but retesting is advised after three years from the initial production date to insure optimum performance.



INNOVATIONS FOR LIVING™

**OWENS CORNING  
COMPOSITE MATERIALS, LLC**  
ONE OWENS CORNING PARKWAY  
TOLEDO, OHIO 43659  
1.800.GET.PINK™  
www.owenscorning.com  
www.composites.owenscorning.com  
Contact:  
SingleEndRovings.ocamericas@owenscorning.com

**EUROPEAN OWENS CORNING  
FIBERGLAS, SPRL.**  
166, CHAUSSÉE DE LA HULPE  
B-1170 BRUSSELS  
BELGIUM  
+32 2 674 8211

Contact:  
SingleEndRovings.ocmea@owenscorning.com

**OWENS CORNING COMPOSITES SOLUTIONS BUSINESS  
ASIA PACIFIC REGIONAL HEADQUARTERS**  
UNIT 01, 02, 05, 39/F, PUDONG KERRY PARKSIDE  
1155 FANG DIAN ROAD, PUDONG, SHANGHAI  
201204, CHINA  
+86-21-6101 9666

Contact:  
SingleEndRovings.ocap@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.

Pub. No. 10010190-B. Owens Corning reserves the right to modify this document without prior notice. ©2012 Owens Corning. All Rights Reserved.

SingleEndRovings\_158B\_ww\_11\_2012\_Rev3